

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

1026

(51) International Patent Classification ⁶ : C04B 26/04 // (C04B 26/04, 14:06, 14:10, 14:22, 24:08, 24:36, 40:06)		A1	(11) International Publication Number: WO 98/21159 (43) International Publication Date: 22 May 1998 (22.05.98)
(21) International Application Number: PCT/GB97/03125 (22) International Filing Date: 13 November 1997 (13.11.97) (30) Priority Data: 9623568.4 13 November 1996 (13.11.96) GB 9702014.3 31 January 1997 (31.01.97) GB (71) Applicant (for all designated States except US): CAIRN HOLDINGS (UK) [-/GB]; Carrington Business Park, Carrington, Manchester M31 4YR (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): POLLITT, Clifford, Bruce [GB/GB]; Cuerdon Cottage, Cuerdon Drive, Thelwall, Warrington WA4 3JU (GB). (74) Agent: URQUHART-DYKES & LORD; Northern Assurance Buildings, Albert Square, Manchester M2 4DN (GB).			(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: MIXTURES OF MATERIALS SETTABLE ON EXPOSURE TO ATMOSPHERE			
(57) Abstract A settable mixture comprises liquid polybutadiene, a flow-enhancing liquid, and particulate material. The mixture may be used as a substrate screed and/or filler for paving, wall and floor elements such as tiles, cobbles, concrete slabs. The mixture can be bagged in a substantially oxygen-free atmosphere ready for use.			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LJ	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

- 1 -

MIXTURES OF MATERIALS SETTABLE ON EXPOSURE TO ATMOSPHERE

THIS INVENTION relates to mixtures of materials.

According to this invention a settable mixture comprises polybutadiene, a flow-enhancing liquid, and particulate material.

The flow enhancing liquid may be a flow-enhancing solvent, and the polybutadiene is in liquid form.

The particulate material may for example comprise dry sand; ground or crushed glass, for example, including recycled glass and ground or crushed television tubes or fluorescent tubes which may include some non-glass material; ground slate or other mineral, for example, granite or stone.

The particulate material may be a mixture of different materials.

Two examples of flow-enhancing liquids are benzene (octane 140 to 165), and aliphatic hydrocarbons of the latter, examples are low aromatic, special boiling point 40/65 to 140/165; special boiling point 40/65 to 140/165 sold by Shell Chemicals U.K. Limited; D type aliphatic hydrocarbons; and BASF 125 sold by BASF.

The mixture is not adhesive, that is it is not tacky to the touch and can, for example, be placed on laid tiles and paving

- 2 -

and swept into the gaps using a brush or the like or placed directly into the gaps between the tiles to act as a filler without sticking to the surface of the tiles.

The particles in the particulate material may be of uniform size or different sizes.

There may be additions, for example colourants and/or reinforcing material e.g. synthetic or carbon fibres.

A typical mixture, has by volume of the total mixture of polybutadiene, flow-enhancer and sand:-

2 to 4% polybutadiene ✓

0.1 to 0.4% benzene (octane 140 to 165) ✓

Balance % silica sand ✓

The mixture may be bagged so as to be contained in an essentially oxygen-free atmosphere.

The invention includes paving, flooring and wall elements secured or spaced apart by said mixture when set.

- 3 -

The invention may be performed in various ways and some specific embodiments with possible modifications will now be described by way of example with reference to the accompanying drawing which shows a bag containing a mixture.

The invention provides a mixture which is settable on exposure to atmosphere (oxygen) and can be used indoors or outdoors for use as a screed or for pointing paving or flooring e.g. stones, cobbles, setts, tiles, concrete or clay or stone slabs; or for pointing wall tiles or bricks.

In general the mixture comprises polybutadiene, a flow-enhancing liquid and particulate material. The polybutadiene is in liquid form.

The flow-enhancing liquid may be a flow-enhancing solvent.

The particulate material which should be substantially dry, may, for example, comprise dry sand; ground or crushed glass, for example, including recycled glass and ground or crushed television tubes or fluorescent tubes which may include some non-glass material; ground slate or other mineral for example granite, stone.

The particulate material may be a mixture of different materials.

Examples of flow-enhancing liquids are benzene (octane

- 4 -

140 to 165), and aliphatic hydrocarbons. Examples are low aromatic special boiling point 40/65 to 140/165; special boiling point 40/65 to 140/165 sold by Shell Chemicals U.K. Limited; D type aliphatic hydrocarbons; and BASF 125 sold by BASF.

The mixture is not adhesive, that is it is not tacky to the touch and can, for example, be placed on laid tiles and paving and swept into the gaps using a brush or the like or placed directly into the gaps between the tiles to act as a filler without sticking to the surface of the tiles.

The glass particles in the particulate material may be of uniform size or different sizes.

The term dry sand includes sand which has been kiln dried and has then absorbed water from the atmosphere. ✓

There may be additions to the mixture, for example a colourant and/or reinforcing material. ✓

A particularly suitable form of liquid polybutadiene is that sold under the name Univest-S by Huls Aktiengesellschaft of Marl, Germany, and ideally occupies the mixture in an amount of between 1½% and 6% by volume. ✓

A particularly preferred sand is kiln dried silica sand of special fraction size (which may have absorbed moisture from the ✓

- 5 -

atmosphere).

Examples of suitable mixtures are:-

- | | | | |
|----|-----------|-----------|--|
| 1. | 2% - 4% | By volume | Polybutadiene ✓ |
| | 0.1-0.4% | By volume | Aroma free Benzene (Octane 140-165) ✓ |
| | Balance % | By volume | Kiln dried silica sand special fraction size ✓ |
| 2. | 2% - 4% | By volume | Polybutadiene ✓ |
| | 0.1-0.4% | By volume | Aroma free benzene 140-165 ✓ |
| | 1% - 5% | By volume | Synthetic or carbon fibres ✓ |
| | Balance % | By volume | Kiln dried silica sand special fraction size ✓ |
| 3. | 2% - 4% | By volume | Polybutadiene |
| | 0.1-0.4% | By volume | Aroma free Benzene 140-165 |
| | 0.1%-0.5% | By volume | Dry colour pigment |
| | Balance % | | Kiln dried silica sand special fraction size |
| 4. | 2% - 4% | By volume | Polybutadiene |
| | 0.1-0.4% | By volume | Aroma free Benzene (140-165) |
| | 1% - 5% | By volume | Synthetic or carbon fibres |
| | 0.1%-0.5% | By volume | Dry colour pigment ✓ |
| | Balance % | | Kiln dried silica sand special fraction size |

The above examples contain sand as the particulate filler but other materials as referred to above may be used with or in place of the sand.

The mixing is done quickly and preferably by machine, to avoid or limit any setting which would occur due to heat and exposure to atmospheric oxygen.

After mixing, the mixture is placed in bags or other convenient containers, and vacuum packed to remove oxygen (air) and thus suspend the setting process in a substantially oxygen-free

- 6 -

atmosphere until the bag is opened. The mixture may be contained in convenient amounts.

If required, to maintain flexibility in the bag, the extracted air may be replaced by a small volume of an inert gas such as carbon dioxide or nitrogen.

The mixture may be diluted if required, using, for example, vegetable oils.

- 7 -

CLAIMS

1. A settable mixture comprising polybutadiene, a flow-enhancing liquid, and particulate material.
2. A mixture as claimed in Claim 1, in which the particulate material comprises dry sand.
3. A mixture as claimed in Claim 1 or Claim 2, in which the particulate material comprises glass.
4. A mixture as claimed in any preceding claim, in which the particulate material comprises slate.
5. A mixture as claimed in any preceding claim, in which the flow-enhancing liquid comprises an aliphatic hydrocarbon.
6. A mixture as claimed in any of Claims 1 to 4, in which the flow-enhancing liquid comprises benzene.
7. A mixture as claimed in any preceding claim, in which the polybutadiene is in liquid form.
8. A mixture as claimed in any preceding claim, in which the polybutadiene is provided in an amount of between 1½% and 6% by volume of the mixture.
9. A mixture as claimed in any preceding claim, diluted


- 8 -

with a vegetable oil.

10. A mixture as claimed in any preceding claim bagged in a substantially oxygen-free atmosphere.

11. A mixture as claimed in Claim 10, bagged in an inert gas atmosphere.

12. A mixture as claimed in any preceding claim and as described herein with reference to any of the Examples.



INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 97/03125

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C04B26/04 //(C04B26/04, 14:06, 14:10, 14:22, 24:08, 24:36, 40:06)

According to International Patent Classification(IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 146 098 A (MARQUARDT GOTZ) 26 June 1985 see page 4, line 17 - page 5, line 16 see page 6, line 34 - page 7, line 9; claims 1,7,10,11,21 ---	1-10,12
Y	DE 40 35 359 C (V.GUELS) 16 April 1992 see column 3, line 40 - line 63 see column 5, line 39 - column 6, line 43 ---	1-10,12
A	EP 0 294 501 A (ELSNER WILFRIED ;STOCKI HORST (DE)) 14 December 1988 see column 1, line 37 - line 47; claims 1,5 ---	1,2,7,8
A	DE 41 01 032 A (MACK ANTON) 23 July 1992 see claims 1,5 ---	1,3
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

9 March 1998

Date of mailing of the international search report

18/03/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Theodoridou, E

INTERNATIONAL SEARCH REPORT

Inter national Application No

PCT/GB 97/03125

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p> DATABASE WPI Section PQ, Week 8623 Derwent Publications Ltd., London, GB; Class Q31, AN 86-148990 XP002058244 & SU 1 189 745 A (GRISHAEV I G) see abstract </p> <p style="text-align: center;">-----</p>	11

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 97/03125

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0146098 A	26-06-1985	DE 3344783 A	20-06-1985
DE 4035359 C	16-04-1992	AT 121059 T	15-04-1995
		AU 652779 B	08-09-1994
		AU 8617891 A	11-06-1992
		CA 2098394 A	08-05-1992
		CN 1061424 A	27-05-1992
		DE 59105204 D	18-05-1995
		WO 9208679 A	29-05-1992
		EP 0556194 A	25-08-1993
		JP 6501504 T	17-02-1994
		KR 9702026 B	21-02-1997
EP 0294501 A	14-12-1988	NONE	
DE 4101032 A	23-07-1992	NONE	